



INVESTOR IN PEOPLE

The Patent Office
Concept House
Cardiff Road
Newport
South Wales
NP10 8QQ

CERTIFIED COPY OF PRIORITY DOCUMENT

I, the undersigned, being an officer duly authorised in accordance with Section 74(1) and (4) of the Deregulation & Contracting Out Act 1994, to sign and issue certificates on behalf of the Comptroller-General, hereby certify that annexed hereto is a true copy of the documents as originally filed in connection with the patent application identified therein.

I also certify that the attached copy of the request for grant of a Patent (Form 1/77) bears an amendment, effected by this office, following a request by the applicant and agreed to by the Comptroller-General.

In accordance with the Patents (Companies Re-registration) Rules 1982, if a company named in this certificate and any accompanying documents has re-registered under the Companies Act 1980 with the same name as that with which it was registered immediately before re-registration save for substitution as, or inclusion as, the last part of the name of the words "public limited company" or their equivalents in Welsh, references to the name of the company in this certificate and any accompanying documents shall be treated as references to the name with which it is so re-registered.

In accordance with the rules, the words "public limited company" may be replaced by p.l.c., plc, P.L.C. or PLC.

Re-registration under the Companies Act does not constitute a new legal entity but merely subjects the company to certain additional company law rules.

Signed

Andrew Gersey

Dated 27 April 2004

THIS PAGE BLANK (USPTO)

Patents Form 1/77 RN

Patents Act 1977
(Rule 16)

THE PATENT OFFICE

26 JUN 2003

RECEIVED BY FAX

26JUN03 18029-1 000239
P01/7700 0.00-0314883.0**Request for grant of a patent**

(See the notes on the back of this form. You can also get an explanatory leaflet from the Patent Office to help you fill in this form)

The Patent Office

Cardiff Road
Newport
South Wales
NP10 8QQ

1. Your reference

MK/JMP/M03687

2. Patent application number

(The Patent Office will fill in this part)

0314883.0

26 JUN 2003

3. Full name, address and postcode of the or of each applicant (underline all surnames)

NCR International, Inc
1700 South Patterson Boulevard
Dayton
Ohio 45479

Patents ADP number (if you know it)

United States of America

6105449001

If the applicant is a corporate body, give the country/state of its incorporation

United States of America/Delaware

4. Title of the invention

SECURITY LABELLING

5. Name of your agent (if you have one)

"Address for service" in the United Kingdom to which all correspondence should be sent (including the postcode)

Cruikshank & Fairweather
19 Royal Exchange Square
Glasgow
G1 3AE

Brian Williamson et al.

International Patent
NCR Limited Department
206 Marylebone Road
London NW1 6LY

Patents ADP number (if you know it)

547002 1982003

6. If you are declaring priority from one or more earlier patent applications, give the country and the date of filing of the or of each of these earlier applications and (if you know it) the or each application number

Country

Priority application number
(if you know it)Date of filing
(day / month / year)

7. If this application is divided or otherwise derived from an earlier UK application, give the number and the filing date of the earlier application

Number of earlier application

Date of filing
(day / month / year)

8. Is a statement of inventorship and of right to grant of a patent required in support of this request? (Answer 'Yes' if:

a) any applicant named in part 3 is not an inventor, or

b) there is an inventor who is not named as an applicant, or

c) any named applicant is a corporate body.

See note (d))

Yes

9. Enter the number of sheets for any of the following items you are filing with this form.
Do not count copies of the same document

Continuation sheets of this form

Description 17

Claim(s) 4

Abstract 1

Drawing(s) 3

10. If you are also filing any of the following, state how many against each item.

Priority documents

Translations of priority documents

Statement of inventorship and right to grant of a patent (Patents Form 7/77)

Request for preliminary examination and search (Patents Form 9/77)

Request for substantive examination (Patents Form 10/77)

Any other documents
(Please specify)

11.

I/We request the grant of a patent on the basis of this application.

Signature *Cruijkshank & Fairweather* Date 26 June 2003

CRUIKSHANK & FAIRWEATHER

12. Name and daytime telephone number of person to contact in the United Kingdom

Dr Maureen Kinsler
0141 221 5767

Warning

After an application for a patent has been filed, the Comptroller of the Patent Office will consider whether publication or communication of the invention should be prohibited or restricted under Section 22 of the Patents Act 1977. You will be informed if it is necessary to prohibit or restrict your invention in this way. Furthermore, if you live in the United Kingdom, Section 23 of the Patents Act 1977 stops you from applying for a patent abroad without first getting written permission from the Patent Office unless an application has been filed at least 6 weeks beforehand in the United Kingdom for a patent for the same invention and either no direction prohibiting publication or communication has been given, or any such direction has been revoked.

Notes

- If you need help to fill in this form or you have any questions, please contact the Patent Office on 08459 500505.
- Write your answers in capital letters using black ink or you may type them.
- If there is not enough space for all the relevant details on any part of this form, please continue on a separate sheet of paper and write "see continuation sheet" in the relevant part(s). Any continuation sheet should be attached to this form.
- If you have answered 'Yes' Patents Form 7/77 will need to be filed.
- Once you have filled in the form you must remember to sign and date it.
- For details of the fee and ways to pay please contact the Patent Office.

SECURITY LABELLING

The present invention relates to a security marker, and to an item incorporating a security marker. The invention also relates to a system for detecting a security marker.

Security markers are provided to enable an item to be validated. The need for security markers for valuable items, such as documents, is well known. Banknotes typically include advanced security features, such as watermarks, fluorescent inks, security threads, holograms, kinograms, and such like. However, with advances in copying technology, it is becoming more difficult to provide security features, which are difficult to counterfeit, easy to detect, quick to detect in situ, and not too expensive to incorporate in an item.

Chemical and biochemical taggants (also known as labels, markers, or tags) are added to items as markers that can be detected to validate the items. However, to validate such taggants, the taggants typically have to be removed from the item and then analysed. This is both time-consuming and expensive, which renders such taggants inappropriate for on-line, high speed examination.

Optical based techniques have been used for non-visual encoding of a range of products. One of the most widely employed optical labeling strategies uses fluorescent labels, for example labels printed using

fluorescent ink or dye. Fluorescent materials emit light when excited by radiation of a particular wavelength. Information can be encoded by forming marks using fluorescent inks, which information can only be retrieved when the mark is illuminated with radiation of the appropriate wavelength. An example of a particular type of fluorescent ink is described in US 5,256,193. JP 8208976; US 4,736,425; US 5,837,042; US 3,473,027; US 5,599,578; GB 2,258,659; US 6,344,261; and US 4,047,033 describe various security labelling and printing applications. However, known inks and dyes have the disadvantage that they have very broad spectra, which limits the number of inks and dyes that can be used in an item.

It is among the objects of an embodiment of the present invention to obviate or mitigate one or more of the above disadvantages or other disadvantages of the prior art.

According to a first aspect of the present invention there is provided an optically detectable security marker for emitting light at a pre-selected wavelength, the marker comprising: a rare earth dopant and a carrier incorporating the rare earth dopant, the interaction of the carrier and the dopant being such as to provide a fluorescent fingerprint or response that is different from that of the rare earth dopant.

The rare earth element has an intrinsic set of electronic energy levels. The interaction between the carrier and the dopant is such that these intrinsic energy levels change when the dopant is incorporated into the carrier. For example, when the dopant is incorporated into a glass, new bonds are formed in the doped glass, thus altering the electron arrangement and hence the energy levels of absorption and fluorescent emission. Altering the rare earth dopant and/or dopant chelate and /or the composition of the carrier changes these energy levels and hence the observed fluorescent fingerprint.

By virtue of this aspect of the invention an optically detectable security marker is provided that can be tailored to have strong fluorescent light emission at a pre-selected wavelength when illuminated with a particular wavelength of light. This enables a validator to validate the security marker by detecting emission at the pre-selected wavelength in response to radiation at a particular wavelength. Such a security marker is very difficult to replicate by a counterfeiter.

Preferably, the rare earth dopant is a lanthanide.

Preferably, the carrier comprises a glass or a plastic. The carrier in which the rare earth dopant is embedded can readily be produced in a variety of formats, e.g. microbeads or fibres suitable for inclusion in

plastic or paper products. Alternatively they may be an integral part of the polymer matrix forming a product.

Due to the very discrete fluorescence wavelength of a carrier doped with a rare earth element, multiple carriers can be used (or a single carrier doped with multiple rare earth elements), each prepared to have a different pre-selected emission wavelength, so that a security profile comprising multiple wavelengths can be provided in a single item without the different wavelengths overlapping each other. This enables a security marker to be provided that has a security profile selected from a large number of permutations, thereby greatly increasing the difficulty in counterfeiting such a security marker.

The carrier doped with the rare earth ion has a new energy level profile that allows transitions different to those allowed by either the rare earth element or the undoped carrier.

The new energy profile is particularly advantageous for security purposes because it provides narrow emissions at wavelengths not naturally found in either the rare earth element or the undoped carrier. These narrow emissions can be used as part of a security marker.

Preferably a plurality of rare earth dopants is used. One or more of these different rare earth dopants

may have intrinsic fluorescence emissions that are visible to the unaided human eye and one or more may have intrinsic fluorescence emissions that are invisible to the unaided human eye, for example infra-red or ultra-violet fluorescence emissions.

Preferably, the combined effect of the carrier and the rare earth dopant is such as to cause the security marker to emit light that is visible by the unaided eye, for example in the range of 390-700nm.

Preferably, the security marker can be excited by highly selective, high intensity visible light and the resultant emission can be detected in the visible region.

According to a second aspect of the present invention there is provided an item having an optically detectable security feature for emitting light at a pre-selected wavelength, the item comprising: a rare earth dopant and a carrier incorporating the rare earth dopant, the interaction of the carrier and the dopant being such as to provide a fluorescent fingerprint or response that is different from that of the rare earth dopant.

The item may be validated by irradiating the item and detecting emissions at the pre-selected wavelength.

The item may be a fluid. Examples of fluids particularly suitable for use with the invention include fuel, paint, ink and such like.

Preferably, the item is a laminar media item. The laminar media item may be in the form of a web, or in sheet form. Examples of sheet form laminar media items include banknotes and financial instruments such as cheques.

Preferably, the item includes a plurality of security markers, each marker emitting at a different pre-selected wavelength. Alternatively, a marker may include a plurality of rare earth dopants.

In a preferred embodiment, the markers have different concentrations of dopant, so that the intensities of the pre-selected wavelength emissions are different.

By virtue of this feature, the relative emission intensity of different pre-selected wavelengths can be used as a security feature. For example, one pre-selected wavelength intensity may be 100%, another pre-selected wavelength intensity 50%, a third pre-selected intensity 25%, and a fourth pre-selected intensity 50%.

More or less than four wavelengths can be used. This provides a large variety of security profiles, where each profile comprises a ratio of intensities of a plurality of wavelengths. This also makes counterfeiting even more difficult, as the quantities of each dopant must be accurately replicated, in addition to the carrier energy difference.

In one embodiment, the emission from each marker decays over a different time period. By virtue of this feature, the time over which an emission occurs for a particular wavelength can be used as part of a security profile.

According to a third aspect of the invention there is provided a system for validating an item having an optically detectable security feature emitting light at one of a plurality of pre-selected wavelengths, where the security feature has a carrier incorporating a rare earth dopant, the system comprising: means for illuminating the security feature with one or more wavelengths for producing emissions from the rare earth dopant; means for detecting emission from the security feature at a pre-selected wavelength; means for filtering and comparing the detected emission with a security profile for the item; and means for indicating a successful validation in the event of the emission matching the security profile.

Preferably, the means for illuminating the item comprises a pulsed light emitting diode and an illumination filter for ensuring that only a narrow band of wavelengths illuminate the item.

Preferably, the means for detecting emission comprise a detection filter to filter out all wavelengths except the pre-selected wavelength, and a photodiode to

detect the intensity of light passing through the detection filter.

In a preferred embodiment, the illumination means comprises an array of LEDs, each LED having a different illumination filter, so that the item to be validated is illuminated with multiple wavelengths. In such an embodiment, the detection means comprises an array of photodiodes, each photodiode having a different detection filter, so that the emission at each pre-selected wavelength can be determined.

According to a fourth aspect of the invention there is provided a method of validating an item having an optically detectable security feature emitting light at one of a plurality of pre-selected wavelengths, the method comprising the steps of: illuminating the security feature with one or more wavelengths for producing emissions from the rare earth dopant; detecting emission from the security feature at a pre-selected wavelength; filtering and comparing the detected emission with a security profile for the item; and indicating a successful validation in the event of the emission matching the security profile.

According to a fifth aspect of the invention, there is provided an optically detectable security marker for emitting light at a pre-selected wavelength, the marker comprising: a rare earth dopant incorporated within a

carrier material, the dopant and the carrier material being such as to cause emission of visible light in response to optical stimulation by visible light of a pre-determined wavelength.

5 Preferably, the interaction of the carrier and the dopant is such as to provide a fluorescent fingerprint or response that is different from that of the rare earth dopant.

10 According to a sixth aspect of the invention, there is provided a security item that includes an optically detectable security marker for emitting light at a pre-selected wavelength, the marker comprising: a rare earth dopant incorporated within a carrier material, the dopant and the carrier material being such as to cause emission
15 of visible light in response to optical excitation by visible light. Preferably, the security item is a fluid, for example fuel, paint, ink and such like. Alternatively the security item may be a laminar media item, for example banknotes and financial instruments
20 such as cheques. Preferably, the item includes a plurality of security markers, each marker emitting at a different pre-selected wavelength. Preferably, the interaction of the carrier and the dopant is such as to provide a fluorescent fingerprint that is different from
25 that of the rare earth dopant.

10

According to a seventh aspect of the invention, there is provided a security marker comprising a borosilicate based glass, preferably including SiO_2 ; NaO ; CaO ; MgO ; Al_2O_3 0.29; FeO and/or Fe_2O_3 ; K_2O , and B_2O_3 , and a rare earth dopant, preferably a lanthanide. Preferably the glass has a composition of: SiO_2 51.79 wt%; NaO 9.79 wt%; CaO 7.00 wt%; MgO 2.36 wt%; Al_2O_3 0.29 wt%; FeO , Fe_2O_3 0.14 wt%; K_2O 0.07 wt%, and B_2O_3 28.56 wt%, not precluding the use of other glass mixes. The glass and the rare earth ion may be formed into a micro-bead.

Detailed Description

A security marker in which the invention is embodied will now be described by way of example only and with reference to the accompanying drawings, of which:

Figure 1 is a block diagram of a detector arrangement;

Figure 2 is a table showing various excitation wavelengths and corresponding emission wavelengths for a Europium dopant in a borosilicate based glass, and

Figure 3 is a table similar to that of Figure 2 for Europium, but in solution.

The marker comprises a carrier, such as glass or plastic including one or more types of rare earth ion. The interaction of the glass or plastic and the dopant is such that the spectral response of the marker is different from that of the rare earth dopant or the

11

carrier per se. In particular, the interaction between the carrier and the dopant is such that the intrinsic energy levels of the dopant change when it is incorporated into the carrier. For example, when the dopant is incorporated into a glass, new bonds are formed in the doped glass, thus altering the electron arrangement and hence the energy levels of absorption and fluorescent emission. Altering the rare earth dopant and/or dopant chelate and /or the composition of the carrier changes these energy levels and hence the observed fluorescent fingerprint. The preferred dopant is any of the lanthanides except Lanthanum. Preferably the rare earth doped glass is formed into micro-beads that can be included in, for example, a fluid such as ink.

Several methods for doping standard glass compositions with the selected fluorescent rare earth ions can be employed. In one method, test samples of doped glass are prepared by the incorporation of the rare earth ions into the batch composition using the appropriate metal salt. The glass is prepared by heating the batch in a platinum crucible to above the melting point of the mixture. In another method, existing standard glass samples are powdered and mixed with solutions of the fluorescent ions. The glass is lifted out of the solvent, washed and then oven dried.

An example of a glass that could be used as the carrier material for the rare earth dopants is a borosilicate based glass. In particular, a glass that could be used is as follows: SiO_2 51.79 wt%; NaO 9.79 wt%; CaO 7.00 wt%; MgO 2.36 wt%; Al_2O_3 0.29 wt%; FeO , Fe_2O_3 0.14 wt%; K_2O 0.07 wt%, and B_2O_3 28.56 wt%. This can be made by ball milling soda lime beads (100 μm) for 5 minutes to create a powder to help melting and mixing. Then 5g of the crushed soda lime beads, 2g of the B_2O_3 and 3mol% of the rare earth dopant, for example Europium, Dysprosium and Terbium but also others, are ball milled together for, for example, 3 minutes. The resulting powder is then put in a furnace and heated up to 550C. It is left in the furnace at this temperature for about 30 minutes, to ensure that the boric oxide is completely melted. Then the temperature is increased to 1100C for 1 hour to produce a homogeneous melt. The temperature is increased again to 1250C and the molten glass is poured into a brass mould, which is at room temperature, which quenches the glass to form a transparent, bubble free borosilicate glass, doped with a rare earth ion.

The peak emission wavelength for fluorescent emission in the marker depends on the energy levels of the final rare earth doped glass. Altering the weight percentage of the network modifier oxides within the glass matrix will change these levels and hence change

the observed peak fingerprint. Hence, to observe the correct wavelength fingerprint, the glass composition has to be known. Likewise, where two or more rare earth dopants are used, varying the ratios, by mole percentage, of these changes the fluorescence intensity in the detected signal. Peak intensities can be used as part of the encoding scheme and so by varying the dopant levels, there is provided an opportunity to provide even more encoding options.

Figure 1 shows an arrangement for detecting information encoded in accordance with the present invention. This includes a sensor and a platform for supporting an item under test. The sensor has a housing in which are provided an emitter, for example a light emitting diode (LED), at the output of which is provided a narrow band filter. The narrow band filter allows only a very narrow, pre-determined range of wavelengths to be passed. As an example, the filter could be selected to allow a narrow band pass centred on a wavelength of 465nm to pass through it and toward the sample platform. Adjacent to the emitter is a detector, such as a photodiode. At its input is a narrow band filter that allows only a very narrow, pre-determined range of wavelengths to pass through it. As an example, the filter could be selected to allow light centred on a wavelength of 615nm to reach the detector.

In use of this arrangement, light is emitted from the emitter and passed through the first narrow band filter and onto a security item that carries or includes the marker. This light is absorbed by the rare earth dopant, which if it matches the energy levels of the dopant and carrier used causes it to fluoresce. Light emitted from the item is transmitted towards the second filter, and from there, to the detector. Also the emission from each marker decays over a different time period. By virtue of this feature, the time over which an emission occurs for a particular wavelength can be used as part of a security profile. For authentic documents, the light received at the detector should have one or more characteristic features that can be identified. In the event that the detected response has the expected features, the item is identified as being bona fide. In the event that the response is not as expected or is not within an acceptable range of the expected response, the item is identified as being a potential counterfeit.

The spectral emissions of various marker samples have been investigated. As an example, Figure 2 shows a table of the emission wavelengths and intensities for various different excitation wavelengths for a marker comprising of 3mol% EuCl_3 when included in the borosilicate glass described above. By way of

comparison, Figure 3 shows the corresponding results for the $\text{EuCl}_3 \cdot 6\text{H}_2\text{O}$ dopant, but when in solution. From these Figures, it can be seen that in glass the most significant excitation is at 395nm, which emits at 615nm and 590.5nm. The corresponding results for the $\text{EuCl}_3 \cdot 6\text{H}_2\text{O}$ in solution shows that the emission wavelengths here are 592.5nm, 618.5nm, 556.5nm, 536nm and 526nm. Hence the spectral response of the marker at 395nm is significantly different from that of the $\text{EuCl}_3 \cdot 6\text{H}_2\text{O}$ in solution. Also in glass, for excitation at a wavelength of 415nm, there is an output of 615nm and 590.5nm. In contrast for the $\text{EuCl}_3 \cdot 6\text{H}_2\text{O}$ in solution there is effectively no fluorescence at this wavelength. Again, this demonstrates that there is significant and measurable difference caused by the incorporation of the $\text{EuCl}_3 \cdot 6\text{H}_2\text{O}$ in the borosilicate carrier.

Because rare earth ions have well defined and relatively narrow, non-overlapping spectral bands, this means for many applications it is possible to detect the security marker using a single discrete pre-determined excitation wavelength and likewise a single discrete pre-determined detection wavelength. For example, for the EuCl_3 doped borosilicate glass described above, the emitter filter could be selected to be 465nm, and the detector filter could be 615nm. Alternatively, a plurality of stimulating wavelengths could be used. To

do this, a number of different suitable emitter filters would be selected, and a plurality of corresponding filters. These would be included in the arrangement of Figure 1 to allow the simultaneous measurement of optical response at various different wavelengths.

A further advantage of the discrete nature of spectral response of rare earth ions is that a number of species can be combined into the one product for improved security for example 3 mole % Eu + 3 mole % Tb, not precluding other rare earths at different percentages and more than two. Because the response of the various different dopants is relatively discrete, detection of these is simplified. The narrow emission bands also facilitate the spectral selection of the molecules, making the detection system simpler than those required for systems containing multiple dyes. A further advantage is that many rare earth ions require excitation at wavelengths conducive to existing laser diode technologies. This makes online excitation not only possible but compact, robust and long lived. Furthermore, incorporating the rare earth dopants into a suitable carrier, and in particular the glass beads described herein, means that the security marker in which the invention is embodied is extremely stable under adverse chemical, environmental and physical abrasion

17

conditions, thereby ensuring that it has a long lifetime compared to conventional dyes.

5 A skilled person will appreciate that variations of the disclosed arrangements are possible without departing from the invention. For example, whilst only a few rare earth ions have been specifically described, it will be appreciated that there is a wide range of fluorescent rare earth ions that could be used. The number of permutations available is therefore greatly enhanced. In
10 addition, whilst some rare earth ions emit in the UV and IR ranges, it is preferred that both the excitation radiation and the emitted radiation are within the visible range, that is within a wavelength range that is visible to the unaided human eye. Accordingly, the above
15 description of a specific embodiment is made by way of example only and not for the purposes of limitation. It will be clear to the skilled person that minor modifications may be made without significant changes to the operation described.

20

Claims

1. An optically detectable security marker for emitting light at a pre-selected wavelength, the marker comprising
5 a rare earth dopant and a carrier incorporating the rare earth dopant, the interaction of the carrier and the dopant being such as to provide a fluorescent fingerprint that is different from that of the rare earth dopant.
- 10 2. A marker according to claim 1, where the rare earth dopant is a lanthanide.
3. A marker according to claim 1 or claim 2, where the carrier comprises a glass or a plastic.
- 15 4. A marker as claimed in any of the preceding claims wherein the dopant and the carrier material are such as to cause emission of visible light in response to optical excitation by visible light.
- 20 5. An item having an optically detectable security feature for emitting light at a pre-selected wavelength, the item comprising a rare earth dopant and a carrier incorporating the rare earth dopant, the interaction of
25 the carrier and the dopant being such as to provide a

fluorescent fingerprint or response that is different from that of the rare earth dopant.

6. An item according to claim 5, where the item is a fluid.

7. An item according to claim 5, where the item is a laminar media item.

8. An item according to claim 5, wherein the security feature comprises a plurality of security markers, each marker emitting at a different pre-selected wavelength.

9. An item according to claim 8, wherein the markers have different concentrations of dopant or dopants, so that the intensities of the pre-selected wavelength emissions are different.

10. An item according to claim 8 or claim 9, wherein the emission from each marker decays over a different time period.

11. A system for validating an item having an optically detectable security feature emitting light at one of a plurality of pre-selected wavelengths, where the security

20

feature has a carrier incorporating a rare earth dopant,
the system comprising:

means for illuminating the security feature with one
or more wavelengths for producing emissions from the rare
5 earth dopant;

means for detecting emission from the security
feature at a pre-selected wavelength;

means for comparing the detected emission with a
security profile for the item;

10 means for the electronic selection of the photodiode
signals based on the fluorescent lifetime of the detected
signal corresponding to the emitted radiation from the
security marker and;

means for indicating a successful validation in the
15 event of the emission matching the security profile.

12. A system according to claim 11, wherein the means
for illuminating the item comprises a pulsed light
emitting diode and an illumination filter for ensuring
20 that only a narrow band of wavelengths illuminate the
item.

13. A system according to claim 11, wherein the means
for detecting emission comprise a detection filter to
25 filter out all wavelengths except the pre-selected

wavelength, and a photodiode to detect the intensity of light passing through the detection filter.

14. A system according to claim 11, wherein the means
5 for electronic selection of the photodiode signal comprise an electronic filter to filter out all signals except the pre-selected signals corresponding to the long-lived rare earth fluorescent emissions.

10 15. A method of validating an item having an optically detectable security feature emitting light at one of a plurality of pre-selected wavelengths, the method comprising the steps of:

illuminating the security feature with one or more
15 wavelengths for producing emissions from the rare earth dopant;

detecting emission from the security feature at a pre-selected wavelength;

comparing the detected emission with a security
20 profile for the item;

detecting and comparing the electronic signals from the photodiode based on the fluorescent lifetime of the detected signal corresponding to the emitted radiation from the security marker; and

25 indicating a successful validation in the event of the emission matching the security profile.

Abstract

An optically detectable security marker for emitting light at a pre-selected wavelength. The marker comprises a rare earth dopant and a carrier incorporating the rare earth dopant. The interaction of the carrier and the dopant is such that the fluorescent fingerprint of the marker is different from that of the rare earth dopant. The marker may be incorporated into a plurality of items, such as fluids, for example paint, fuel or ink, and laminar products such as paper or banknotes or credit cards.




Figure 1: Example of an arrangement for in-situ validation of security label

THIS PAGE BLANK (USPTO)

1.7831-1.0

Excitation wavelength (nm)	Emission wavelength (nm)	Fluorescent intensity
395	535	14.433
395	590.5	82.873
395	615	285.211
395	654	13.332
415	590.5	11.469
415	615	30.916
465	615	175.781
465	590.5	38.013
535	615	28.495

Figure 2: Europium in borosilicate based glass

THIS PAGE BLANK (SEE 10,

Excitation wavelength (nm)	Emission wavelength (nm)	Fluorescent intensity
395	526	1.746
395	536	2.495
395	556.5	8.633
395	592.5	85.608
395	618.5	30.277
415	-	-
465	594	2.288
465	616.5	0.793
465	700.5	3.915
535	592	1.126

Figure 3: Europium in aqueous solution

THIS PAGE BLANK (USPTO)